

75 - INOCULANT (SNAM - BIAL)

ELEMENT	PERCENTAGE
SILICON	60 - 70%
CALCIUM	1.00 - 1.50 %
ALUMINIUM	0.80 - 1.50%
RARE EARTHS	0.60 - 1.0%
BISMUTH	0.80 - 1.0%
IRON	REST

SIZING :

6 - 12 MM 2 - 6 MM 0.50 - 2.0 MM 0.20 - 0.70 MM

SUGGESTED APPLICATION:

- SNAMBIAL** is best suited for inoculation of Ductile iron
- SNAMBIAL** helps in increase of number of Nodules
- Amount of Ferrites are increased in the castings
- Especially suitable for thin walled Castings.

PACKAGING:

25 Kgs . Paper Bags, 50Kgs. HDPE Bags 250 Kgs. Steel Drums, 1000 Kgs. Big Bags.

NOTE

Addition at metal stream into the pouring ladle gives good dissolution and best results.

Snam Alloys Pvt. Ltd.

Kariamanickam Village, Nettapakkam, Pondicherry - 605 106. India. Phone : 91-413-2699440, 2699106. Fax : 91-413-2699199
e.mail : snam@md2.vsnl.net.in, snamgroup@gmail.com, website:<http://www.sapl.co.in>

The information given in this data sheet is based upon our current knowledge and is intended to provide general notes about our products and their uses. It should not be construed, therefore, as guaranteeing specific properties of the products described or their suitability for a particular application, nor as providing complete instructions for use.

