

75 - INOCULANT (SNAM - HIAL)

ELEMENT	PERCENTAGE
SILICON	70 - 75%
CALCIUM	0.50 - 1.0%
ALUMINIUM	3.50 - 4.50%
IRON	REST

SIZING :

6 - 12 MM.

2 - 6 MM

0.50 - 2.0 MM

0.20 - 0.70 MM

SUGGESTED APPLICATION:

- SNAMHIAL** is best suited for inoculation of Ductile iron.
- SNAM HIAL** provides a high inoculation level due to the effective inoculating elements such as calcium and aluminium
- SNAMHIAL** helps in increase of eutectic cells
- Inhibits white solidification and carbide formation in thin wall sections also.
- Extended pouring time as **SNAM HIAL** delays the inoculation fading.

PACKAGING:

25Kgs . Paper bags, 50Kgs. Bags, 100 Kgs. Steel Drums, 250 Kgs. Steel Drums, 1000Kgs. Big Bags.

NOTE

Addition at metal stream into the pouring ladle gives good dissolution and best results.

Snam Alloys Pvt. Ltd.

Kariamanickam Village, Nettapakkam, Pondicherry - 605 106. India. Phone : 91-413-2699440, 2699106. Fax : 91-413-2699199
e.mail : snam@md2.vsnl.net.in, snamgroup@gmail.com, website:<http://www.sapl.co.in>

The information given in this data sheet is based upon our current knowledge and is intended to provide general notes about our products and their uses. It should not be construed, therefore, as guaranteeing specific properties of the products described or their suitability for a particular application, nor as providing complete instructions for use.

