

## 75 - INOCULANT (SNAM - LACAL)

ELEMENT	PERCENTAGE
SILICON	50 - 60%
CALCIUM	1.80 - 2.50%
ALUMINIUM	0.80 - 1.25%
LANTHANUM	1.75 - 2.25%
IRON	REST

### SIZING :

6 - 12 MM    2 - 6 MM    0.50 - 2.0 MM    0.20 - 0.70 MM

### SUGGESTED APPLICATION:

- SNAMLACAL** is best suited for inoculation of Ductile and Vermicular iron.
- SNAMLACAL** is very effective for chill reduction
- SNAMLACAL** is very effective for shrinkage control
- SNAMLACAL** helps in minimizing micro porosities
- SNAMLACAL** helps in controlling the effect of undesirable elements in iron

### PACKAGING:

25Kgs . Paper bags, 50Kgs. Bags, 100 Kgs. Steel Drums, 250 Kgs. Steel Drums, 1000Kgs. Big Bags.

### NOTE

Addition at metal stream into the pouring ladle gives good dissolution and best results.

## Snam Alloys Pvt. Ltd.

Kariamanickam Village, Nettapakkam, Pondicherry - 605 106. India. Phone : 91-413-2699440, 2699106. Fax : 91-413-2699199  
e.mail : [snam@md2.vsnl.net.in](mailto:snam@md2.vsnl.net.in), [snamgroup@gmail.com](mailto:snamgroup@gmail.com), website:<http://www.sapl.co.in>

The information given in this data sheet is based upon our current knowledge and is intended to provide general notes about our products and their uses. It should not be construed, therefore, as guaranteeing specific properties of the products described or their suitability for a particular application, nor as providing complete instructions for use.

