

## 75 - INOCULANT (SNAM - X BACAL)

ELEMENT	PERCENTAGE
SILICON	60 - 65%
CALCIUM	0.80 - 1.50 %
ALUMINIUM	0.80 - 1.50%
BARIUM	7.0 - 11.0%
IRON	REST

### SIZING :

6-12 MM.          2-6 MM          0.50 - 2.0 MM          0.20 - 0.70 MM

### SUGGESTED APPLICATION:

- SNAM X BACAL** is best suited for inoculation of Ductile iron.
- SNAM X BACAL** is very effective as a ladle inoculant
- SNAM X BACAL** has a long fade time.
- SNAM X BACAL** helps in improving nodularity and nodule count.
- SNAM X BACAL** helps in reduction of carbide formation.

### PACKAGING:

25Kgs . Paper bags, 50Kgs. Bags, 100 Kgs. Steel Drums, 250 Kgs. Steel Drums, 1000Kgs. Big Bags.

### NOTE

Addition at metal stream into the pouring ladle gives good dissolution and best results.

## Snam Alloys Pvt. Ltd.

Kariamianickam Village, Nettapakkam, Pondicherry - 605 106. India. Phone : 91-413-2699440, 2699106. Fax : 91-413-2699199  
e.mail : [snam@md2.vsnl.net.in](mailto:snam@md2.vsnl.net.in), [snamgroup@gmail.com](mailto:snamgroup@gmail.com), website:<http://www.sapl.co.in>

The information given in this data sheet is based upon our current knowledge and is intended to provide general notes about our products and their uses. It should not be construed, therefore, as guaranteeing specific properties of the products described or their suitability for a particular application, nor as providing complete instructions for use.

